Appl. No. 09/759,854 Amdt. dated February 9, 2004 Amendment under 37 CFR 1.116 Expedited Procedure Examining Group

## Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

## **Listing of Claims:**

- 1. (Canceled)
- 2. (Canceled)
- 3. (Canceled)
- 4. (Canceled)
- 5. (Canceled)
- 6. (Canceled)
- 7. (Canceled)
- 8. (Canceled)
- 9. (Canceled)
- 10. (Canceled)
- 11. (Canceled)
- 12. (Canceled)
- 13. (Canceled)
- 14. (Canceled)
- 15. (Canceled)
- 16. (Canceled)
- 17. (Canceled)
- 18. (Previously presented) A method of forming a layer on a substrate in a process chamber, the method comprising:

forming a fluorinated silicate glass layer over the substrate;

forming a patterned photoresist layer over the fluorinated silicate glass layer; etching the fluorinated silicate glass layer according to the patterned photoresist

layer;

Appl. No. 09/759,854 Amdt. dated February 9, 2004 Amendment under 37 CFR 1.116 Expedited Procedure Examining Group

removing the photoresist layer and substantially simultaneously introducing nitrogen dopants into the fluorinated silicate glass layer by subjecting the photoresist layer and the fluorinated silicate glass layer to a plasma formed from a nitrogen-containing gas;

wherein the plasma contains no oxygen species.

- 19. (Original) The method of claim 18 wherein the nitrogen-containing gas is selected from the group consisting of N<sub>2</sub> and NH<sub>3</sub>.
- 20. (Original) The method of claim 18 wherein the nitrogen-containing gas comprises at least one of N<sub>2</sub> and NH<sub>3</sub>.
  - 21. (Canceled)
- 22. (Original) The method of claim 18 wherein nitrogen dopants are incorporated into the fluorinated silicate glass layer in a region near a surface of the fluorinated silicate glass layer which is exposed to the plasma formed from the nitrogen-containing gas.
- 23. (Original) The method of claim 22 wherein the region near the surface of the fluorinated silicate glass layer has a nitrogen content of less than about 10 at. %.
- 24. (Original) The method of claim 23 wherein the region near the surface of the fluorinated silicate glass layer has a nitrogen content of about 1 to about 5 at. %.
- 25. (Original) The method of claim 18 further comprising forming a barrier layer over the nitrogen-containing fluorinated silicate glass layer.
- 26. (Previously presented) The method of claim 25 wherein the barrier layer comprises at least one of silicon-carbon, silicon nitride, tantalum and tantalum nitride.
- 27. (Original) The method of claim 25 further comprising forming a metal layer over the barrier layer.
- 28. (Original) The method of claim 27 wherein the metal layer comprises copper.
  - 29. (Canceled)
  - 30. (Canceled)